



TECHNICAL INFORMATION

KALEX[®] 49563/59563 (formerly KALEX[®] 19563) Filter and Permeator Bonding Adhesive System

PRODUCT DESCRIPTION

KALEX 49563/59563 is a two-component polyurethane system designed for reverse osmosis production (RO). The adhesive binds and seals the filaments in ultra filtration, nano filtration and RO filters.

KALEX adhesive systems offer the flexibility of room temperature processing. This system is hydrophobic and features both excellent membrane wetting and sag resistance.

KALEX 49563/59563 is a hydrophobic polyurethane designed for both wet and dry RO filters. It has a convenient 1:1 mix ratio. All the components are listed in FDA 175.105 or 175.300 and 170.39 (reference 99-015).

MIXING AND CURING SCHEDULE

The production of the desired polyurethane requires accurate measurement of the two components and adequate mixing. In general, hand-mixing small production runs is easily accomplished by weighing the two components. Machine mixing utilizes the volumetric ratio. Most machines are calibrated by weighing the components and adjusting the volume ratio. Larger volume hand mixing is easily controlled by filling pre-measured buckets to the indicated heights. The mix ratios are shown below.

<u>Ratio</u>	<u>49563</u>	<u>59563</u>
By weight	100	88
By volume	100	100

The gel time and work-life vary with the mass and the ambient temperature. Larger masses and higher temperatures reduce the work-life. Lower temperatures extend the work life.

The cure schedule is dependent upon the temperature. The recommended cure schedule will vary with the desired properties. The recommended schedule to achieve the typical properties are shown below:

Cure 3-7 days at @ 25 °C (77°F)

TYPICAL UNCURED PROPERTIES

	<u>49563</u>	<u>59563</u>	<u>Mixed</u>
Color	Light Brown	Translucent White	Pale Yellow
Viscosity @ 25 °C, cps	8,000	9,000	9,000
Weight per gal., lbs.	8.83	7.75	8.29
Specific gravity @ 25°C	1.05	0.93	0.99
Gel time, minutes 100 gm mass @ 25°C	-----	-----	45
Shelf Life (in separate sealed containers), months	6	6	-----

TYPICAL CURED PROPERTIES

<u>Test</u>	<u>Property</u>
Hardness, Shore A	80

STORAGE AND HANDLING

These materials should be stored in a dry environment within a moderate temperature range. Extended exposure to temperatures above 35°C begins to degrade the 49563. Avoid exposing either component to moisture.

Moisture reacts with the 49563 to create minor levels of by products. Low levels will not degrade the final polyurethane. Moisture contamination of the 59563 will cause some gas bubbles in the cast polyurethane. Purge the container with nitrogen or dry air before closing to maintain the storage life.

When using meter-mixed dispense equipment (MMD) machines, reservoir should be blanketed with nitrogen or dry air to avoid moisture and other contamination.

Avoid contamination with oxidized metals (such as copper, brass, or mild steel), and rust or other metal oxides. The stability of the product is greatly reduced by materials such as strong acids or bases, sulfur compounds, amines, or reducing agents of any type.



TECHNICAL INFORMATION

SAFETY

These materials are intended for industrial use only and the practices of good housekeeping, safety and cleanliness should be followed before, during and after use.

Although the system contains low volatility materials, nevertheless, care should be taken in handling. Adequate ventilation of work place and ovens is essential.

These materials may cause dermatitis in susceptible individuals. Keep off skin and out of eyes. In case of accidental skin contact, wash thoroughly with soap and water. In case of eye contact, flush eyes thoroughly with water and consult a physician immediately.

Refer to Material Safety Data Sheets for additional information.

ADDITIONAL INFORMATION

Visit our web site at:

www.royaladhesives.com

Contact us at:

Royal Adhesives and Sealants, LLC
2001 W. Washington Street
South Bend, IN 46628
Phone: 800-999-GLUE
Fax: 574-246-5425
Web: www.royaladhesives.com

NOTE

The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchases will be subject to a separate agreement, which will not incorporate this document.